

A polyurea thickened, medium viscosity, synthetic hydrocarbon grease specially fortified for the protection of electrical contacts. Benefits include insertion force reduction, fretting corrosion protection and high temperature performance.

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-40 to 175	
Thickener		Polyurea	
Base Oil	Type	PAO/Alkylated Naphthalene	
	Kinematic Viscosity	100°C	10 cSt
		40°C	66 cSt
	Viscosity Index		134
	Flash Point	°C	258
	Pour Point	°C	-45
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		Tan, Smooth	
Penetration (1/10 mm)	Unworked	0	278
	Worked	60	293
	NLGI Grade		2
Oil Separation	24 hour(s)	100°C	0.97 %
Evaporation		100°C	0.13 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1904)